

DANTHANE® I 25KS

DESCRIPTION

DANTHANE® 125KS is a polyester based, aromatic TPU, already coloured in black. DANTHANE® 125KS is best suitable for coatings, that must show high flexibility also at low temperatures. DANTHANE® 125KS is mainly used at the production of black coloured transport elements (transport and conveyor belt coatings).

PRODUCT CHARACTERISTIC

	Values	Method
Aspect	Black coloured pearl granule (colour RAL 9005)	
Density	1,23 g/cm ³ at 20 °C	DIN 53.479
Melt Flow Index (MFI)	Acc. to customer specification	
Shore hardness	85 A	DIN 53.505
Melting range	130 – 140 °C	KOFLER
Softening range	125 – 130 °C	KOFLER
Hydrolysis resistance	Good	
Solubility	Good soluble in DMF and THF. The resistance of the films produced with DANTHANE® 125KS to all organic solvents is good, respectively the films will show a swelling behaviour by the influence of these solvents.	

MECHANICAL VALUES

	Values	Method
Tear strength	25 MPa	DIN 53.504
Elongation at break	520 %	DIN 53.504
Modulus 100 % elongation	7,5 MPa	DIN 53.504
Modulus 200 % elongation	9,0 MPa	DIN 53.504
Modulus 300 % elongation	11,0 MPa	DIN 53.504
Compression set (70 hrs./23 °C)	40 %	DIN 53.517
Compression set (24 hrs./70 °C)	85 %	DIN 53.517
Abrasion loss	40 mm ³	DIN 53.516
Glass transition temperature (T _g) (DSC, 10 °C/min.)	-28 °C	DIN 51.007

APPLICATION

DANTHANE® 125KS is applied at the hot melt coating of industrial textiles. The coated textiles are used for transport and drive sections. DANTHANE® 125KS is mainly applied by calender and extrusion. The product can be grinded to powder and so it is also suitable for sinter and dot point coating. Concerning powder we refer to the type DANTHANE® 125KS-Powder.

PROCESSING

To get optimum results by the processing of DANTHANE® 125KS the product should be pre-dried. For drying we recommend to use tumble, vacuum and circulation dryers. The granules should be dried at a temperature range of 90 °C to 100 °C for 2 hours. DANTHANE® 125KS is mainly processed by flat film extrusion as well as by melt calender coating. For the coating of textiles we also deliver the corresponding impregnations and primers with the DANCOLL® products.

COMPATIBILITY

DANTHANE® 125KS is an already black coloured TPU-granule. This TPU granule has also a compatibility to PVC coating raw materials and will be applied for this reason as PVC modifier. Also additive TPU masterbatches can be added. Here we refer to the additive TPU masterbatches of the DANADD® -MB-range.

STORAGE

If correctly stored in a dry and cool place in its original packing, this product can be stored for at least 6 months. The product needs to be protected from humidity.

PRODUCT SAFETY

DANTHANE® 125KS is under normal hygienic processing conditions a harmless material. If larger quantities are being processed in the melt, vapour extraction must be ensured.

* For further data we refer to our Safety Data Sheet

PHYSIOLOGICAL CHARACTERISTICS

With regard to physiological aspects, the product DANTHANE® 125KS is a harmless material to a large extent. For the release for applications in the food and medical sector it must be fulfilled corresponding requirements. If you intend to use the product in these two sectors, we kindly ask you to contact us. This product meets the positive list acc. to FDA, 21CFR, §177/2600, for applications in the food area.

RECYCLING

Clean and uncontaminated waste of DANTHANE® 125KS, which was separated from the substrate, may be grinded and reused as grinding material or may be added to new material.

PACKAGING


25 kg antistatic, special bags packed on pallets of 750 kg. The pallets are wrapped with PE shrink films.





DANQUINSA
GMBH

STÖRRENSTR.30
72135 DETTENHAUSEN
GERMANY

Post office box 147
72133 DETTENHAUSEN
GERMANY

 : +49 (0)7157 5225-0

 : +49 (0)7157 5225-22

 : info@danquinsa.com

WWW.DANQUINSA.COM

STAND 08/2022