

DANTHANE® I 26KB-POWDER

DESCRIPTION

DANTHANE® 126KB-Powder is a polyester based aromatic TPU, already coloured in blue. This TPU powder is suitable for sinter coating, mainly at the production of technical textiles. It can be reached medium-hard surface coatings, like they will be needed for example for the production of transport and conveyer belts, flat belt materials, flexible containers and textile lining materials. DANTHANE® 126KB-Powder can be used as intermediate layer and top coat. Very often DANTHANE® 126KB-Powder is used as intermediate layer and then, as top coat, the transparent type DANTHANE® 126K-Powder is used.

PRODUCT CHARACTERISTIC

	Values	Method
Aspect	Blue coloured powder (colour RAL 5015)	
Powder grit size	50 – 500 µ	
Density	1,20 g/cm ³ at 20 °C	DIN 53.479
Melt flow index	190 °C/10,0 kg/10 min.: 65 – 95 g	
Moisture content	< 0,5 %	
Shore hardness	94 A -> 36 D	DIN 53.505
Melting range	165 – 175 °C	KOFLER
Softening range	140 – 160 °C	KOFLER
Hydrolysis resistance	Very good	
Chemical resistance	Good resistant against oil, fuel, ester, ketone and hydrogen chloride.	

MECHANICAL VALUES

	Values	Method
Tear strength	35 MPa	DIN 53.504
Elongation at break	420 %	DIN 53.504
Modulus 20 % elongation	5 MPa	DIN 53.504
Modulus 100 % elongation	13 MPa	DIN 53.504
Modulus 300 % elongation	15 MPa	DIN 53.504
Tear propagation resistance	90 kN/m	DIN 53.515
Abrasion loss	30 mm ³	DIN 53.516
Resilience	37 %	DIN 53.512
Compression set (70 hrs./23 °C)	25 %	DIN 53.517
Compression set (24 hrs./70 °C)	60 %	DIN 53.517
Glass transition temperature (Tg) (DSC, 10 °C/min.)	-22 °C	DIN 51.513
Tear strength after 21 days (Immersion in water at 80°C)	25 – 30 MPa	DIN 53.504
Elongation at break after 21 days (Immersion in water at 80 °C)	450 – 530 %	DIN 53.504



APPLICATION

DANTHANE® 126KB-Powder is applied at the hot melt coating of industrial textiles. The coated textiles are used for transport and drive sections. This TPU powder, coloured in blue, can be used at the coating as intermediate layer and top coat. Very often DANTHANE® 126KB-Powder is used as intermediate layer and then, as top coat, the transparent type DANTHANE® 126KB-Powder is used. For the coating of textiles we also deliver the corresponding impregnations and primers with the DANCOLL® products.

PROCESSING

DANTHANE® 126KB-Powder is suitable for a lot of powder coating applications. We recommend DANTHANE® 126KB-Powder for:

- sinter coating
- dot point coating
- double dot point coating
- powder coating
- powder impregnation

Before the textiles will be coated, an impregnation and primer must put on. Concerning this we refer to the DANCOLL® product range.

COMPATIBILITY

DANTHANE® 126KB-Powder can be modified with flow regulation agents and additive wax, respectively stearates. This TPU powder has also a good compatibility to PVC-coating raw materials and will be applied for this reason as PVC modifier.

STORAGE

If correctly stored in a dry and cool place in its original packing, this product can be stored for at least 6 months. The product needs to be protected from humidity.

PRODUCT SAFETY

DANTHANE® 126KB-Powder is under normal hygienic processing conditions a harmless material. If larger quantities are being processed in the melt, vapour extraction must be ensured.

* For further information we refer to our Safety Data Sheet

PHYSIOLOGICAL CHARACTERISTICS

In its chemical constitution DANTHANE® 126KB-Powder corresponds to the recommendations of BGA (Bundesgesundheitsamt) and FDA (FOOD and DRUG-ADMINISTRATION) for the production of food and utensils. The terms, that are mentioned in the recommendations, must be observed.

RECYCLING

Clean and uncontaminated waste of DANTHANE® 126KB-Powder, which was separated from the substrate, may be grinded and reused as grinding material or may be added to new TPU material.



PACKAGING


25 kg aluminium moisture proof multilayer bags, packed on pallets of 500 kg. Additionally, PE-lined cardboard bigbags of 700 kg net weight are available.





DANQUINSA
GMBH

STÖRRENSTR.30
72135 DETTENHAUSEN
GERMANY

Post office box 147
72133 DETTENHAUSEN
GERMANY

 : +49 (0)7157 5225-0

 : +49 (0)7157 5225-22

 : info@danquinsa.com

WWW.DANQUINSA.COM

STAND 08/2022